

Fluxbond Specifications

Mineral Development LLC
PO Box 15872
Little Rock, Arkansas 72231

TYPICAL DATA SHEET

FLUXBOND 30 ARKANSAS NEPHELINE SYENITE

CHEMICAL ANALYSIS

Silicon Dioxide (SiO ₂)	59.80
Aluminum Dioxide (Al ₂ O ₃)	17.40
Iron (ferric) Oxide (Fe ₂ O ₃)	2.50
Iron (ferrous) Oxide (FeO)	1.40
Titanium Dioxide (TiO ₂)	0.93
Calcium Oxide (CaO)	1.40
Magnesium Oxide (MgO)	0.94
Manganese Oxide (MnO)	0.29
Sodium Oxide (Na ₂ O)	6.20
Potassium Oxide (K ₂ O)	6.30
Other Trace Elements	0.52
Loss of Ignition*	1.10

* @ 1000 C

PHYSICAL PROPERTIES

Raw Color	Light Gray
Hardness	5.5 – 6 (Mohs) Range
PH	9
Specific Gravity	2.63
Bulk Density: Wt.lbs./ft ³ STM C29	90
Dry Brightness (GE, ASTM E 97)	27

TYPICAL SCREEN ANALYSIS

Retained (Wet)	
50 Mesh	30
100 Mesh	27

Notice: All data given and statements made herein are believed to be typical data; however, no guarantee of their accuracy is made or implied. Our products are sold on the condition that the user will evaluate the material, as well as our formulas and recommendations, to determine their suitability for the purpose.